



CARLISLE'S **SURE-SEAL® AND SURE-WHITE®** **LAP SEALANT**



Overview

Let Carlisle simplify your next EPDM installation with its Sure-Seal and Sure-White Lap Sealants. Sure-Seal and Sure-White Lap Sealants are heavy-bodied trowel- or gun-consistency materials used in conjunction with roofing system materials. Their primary use is to seal the exposed edges of EPDM membrane splices. Lap Sealants are extremely durable, and their cured rubber consistency enables them to expand and contract with the membrane.

Sure-Seal Lap Sealant is to be used to seal splice edges of cured Sure-Seal EPDM and uncured EPDM Elastoform Flashing. Sure-White Lap Sealant seals the splice edges of cured Sure-White EPDM and uncured Sure-White Elastoform Flashing.

Intended Uses

Sure-Seal and Sure-White Lap Sealants are primarily used to seal the exposed edges of EPDM membrane splices.

Features and Benefits

- Various application methods - trowel, caulk gun, etc.
- Cured rubber consistency
- Able to expand and contract with EPDM membrane
- Seals exposed edges of EPDM and provides a durable barrier to weather extremes

Coverage Rates

22' (6.7 m) per tube or 256' (78 m) per gallon using a 5/16" (8 mm) bead.

Application*

1. All surfaces to be sealed with Lap Sealant must be firm, dry and free of oil, talc dust and other foreign materials.
2. After seams are completed with the proper splicing materials, clean the rubber to remove all foreign materials by wiping with a Carlisle HP Splice Wipe (or equivalent) dampened with Weathered Membrane Cleaner. Note: Permeation resistant gloves (that meet ANSI/ISEA 105-2005) are recommended while using cleaner.
3. Apply a 5/16" (8 mm) bead of Lap Sealant along the exposed edge of the membrane.
4. Using the feathering tool supplied with the sealant, feather the sealant bead so the high point is above the offset of the splice and the edges are feathered onto the deck.
5. Lap Sealant must be applied and feathered on all splice edges by the end of the working day. [Adhesive membrane splices must be allowed to age at least two hours before Lap Sealant is applied. SecurTAPE™ splices between cured membrane and Elastoform Flashing may be sealed immediately.]

* REVIEW CURRENT CARLISLE SPECIFICATIONS AND DETAILS FOR SPECIFIC APPLICATION REQUIREMENTS.



CARLISLE'S SURE-SEAL AND SURE-WHITE LAP SEALANT

Precautions

- Review the applicable Material Safety Data Sheet for complete safety information prior to use.
- Lap Sealants are FLAMMABLE. They contain petroleum distillates that are dangerous fire and explosion hazards when exposed to heat, flame or sparks. Store and use away from all sources of heat, flame or sparks. Do not smoke while applying. Do not use in confined or unventilated area. Vapors are heavier than air and may travel along ground to a distant ignition source and flash back. A red caution label is required when shipping.
- Avoid breathing vapors. Keep container closed when not in use. Use with adequate ventilation. If inhaled, remove to fresh air. If not breathing, perform artificial respiration. If breathing is difficult, give oxygen. Call a physician immediately.
- If swallowed, DO NOT INDUCE VOMITING. Call a physician immediately.
- Avoid contact with eyes. Safety glasses or goggles are recommended. If contact with eyes occurs, immediately flush eyes with plenty of water for at least 15 minutes. Contact a physician immediately.
- Avoid contact with skin. Wash hands thoroughly after handling. In case of contact with skin, thoroughly wash affected area with soap and water.

Note: Permeation-resistant gloves (that meet ANSI/ISEA 105-2005) are to be worn when using this product to protect hands from irritating ingredients.
- Follow Carlisle's recommended splice instructions. DO NOT USE as splice cement between membranes.
- Jobsite storage temperatures in excess of 90°F (32°C) may affect product shelf life. Should the Lap Sealant be stored at temperatures below 60°F (15°C), restore to room temperature prior to use.
- By using an excessively wet solvent cloth while cleaning the splice edge, solvent may be left in the offset of the membrane sheets. To avoid causing this problem, use a damp rag and make sure the Weathered Membrane Cleaner is completely flashed off the area before Lap Sealant application.
- If applied during periods of cold, dampness or high humidity, it is possible that evaporation of solvents will be substantially reduced, resulting in some slight membrane swelling. This would be further aggravated should the sealant be applied in an unusually heavy coat.
- Coverage rates are average and may vary due to conditions on the jobsite.
- KEEP OUT OF THE REACH OF CHILDREN.

Sure-Seal and Sure-White Lap Sealant

Typical Properties and Characteristics*

Color	Sure-Seal – black Sure-White – white
Solids	Sure-Seal – 63% Sure-White – 55%
Flash Point	Sure-Seal 40°F (4°C) Tag Open Cup Sure-White 52°F (11°C) Closed Cup
Service Temp.	-60°F to 180°F (-51°C to 82°C)
Specific Gravity	Sure-Seal – 1.03 Sure-White – 1.16
Cold Weather Flex.	Excellent
Resistance to:	
Staining	Excellent
General Weathering	Excellent
Ozone	Excellent
Ultraviolet Radiation	Excellent
Slump	Very Good
Water	Excellent
Acid	Good
Alkali	Good
VOC	Sure-Seal – 395 grams/liter Sure-White – 448 grams/liter
Average Net Weight/gallon	Sure-Seal – 8.58 lbs. (1.03 Kg/l) Sure-White – 9.94 lbs. (1.19 Kg/l)
Packaging	25 Tubes/Carlton, 5-gallon pails
Shelf Life	1 year

- * Typical properties and characteristics are based on samples tested and are not guaranteed for all samples of this product. This data and information is intended as a guide and does not reflect the specification or specification range for any particular property of this product.